To meet a variety of different market demands, SCHOTT offers its well-known B 270[™] crown glass in sheet glass form.

B 270[™], manufactured by the up-draw method, offers high stability with respect to solarization in combination with high transmission in the visible wavelength range. It has a fire-polished surface and high chemical stability.

B 270[™] is available in a wide range of thicknesses, a variety of in-stock sizes and shapes, and custom shapes. It can also be custom processed upon request.



Applications



CD / DVD pick up digital projection

- High transmittance
- Cost efficient processing due to wide thickness range




CRT door phone

- High solarization stability
- Fire-polished surface for use without polishing



Surface acoustic wave type touch panel

- Low acoustic attenuation
- High transmittance



Monitor glass for coaters

- High transmittance
- Cost efficient process monitoring



Gifts

- High transmittance
- Crystal-like appearance
- Fusible with adapted glasses

Technical Data

recilifical Bata	
Dimensions	406 mm x 258 mm, 840 mm x 800-920 mm,
	1680 mm x 800-920 mm (16.0 in x 10.1, 33 in x 31.5-36.2 in,
	66.1 in x 31.5-36.2 in) other sizes upon request
Thicknesses	0.8 mm up to 17.0 mm < 0.8 mm on request
Luminous transmittance T_{vD65} (d = 2.0 mm)	91.7 %
Coefficient of mean linear thermal expansion	9.4 · 10 ⁻⁶ K ⁻¹
α (20 °C; 300 °C) (static measurement)	
Transformation temperature Tg	533 °C
Dielectric constant ε _r at 1MHz	7.0
Refractive index n _D	1.5229
Density ρ	2.55 g/cm ³

Advanced Materials SCHOTT North America, Inc. Phone: +1 914 831-2200 555 Taxter Rd Elmsford, NY 10523 USA

Fax: +1 914.831.2201 info@us.schott.com www.us.schott.com

